KEP 960N



Ethylene Propylene Diene Terpolymer

KUMHO POLYCHEM

Product Data Sheet

Revision Date

Revision No.

12/02/2020

4

Product Description		Features	
molecular weight distri It can be used to wind	nded EPDM rubber with medium bution, high ethylene contents. ow seals, extruded goods in gendings in general, washing machin.	High load eral Superior e Good ph with SBR	processability ysical properties blending
Test items	Sale Specifications	Unit	Test Method
Volatile Matter	Max 0.75	wt %	ASTM D5668
Mooney Viscosity ML(1+8)@125 ℃	49.0 ± 6.0	MU	ASTM D1646
Ethylene Contents	70.0 ± 3.0	wt %	ASTM D3900
ENB Contents	5.7 ± 1.0	wt %	ASTM D6047
Oil Contents	50.0 ± 3.0	phr	Internal Method
Other Products Fea	tures		
Product Form	Bale		
Packaging	35 kg/Bale in Carton/Mesh Box, EOM film 840 kg(35 kg × 24)		
Shelf Life	24 months from date of production at room temperature in dry condition, exposure to light has to be avoided		
The Others	RoHS Free		
Contact Informatio	n		
Head Office	8F, East Wing, Signature Tower, #100 Cheonggyecheon-ro, Jung-gu, Seoul, Korea 82-2-6961-0000		
Plant	613 Sandanjungang-ro, Yeosu, Jeonnam, Korea 82-61-688-2822		